

Properties of Insulation Materials

Properties	ASTM Method	PVC	Semi Rigid PVC	Polyethylene	Foamed Polyethylene	Polypropylene	Foamed Polypropylene	Polyurethane	HYTREL®	NYLON	TPE
Specific Gravity	D-792	1.15 - 1.68	1.37	0.90 - 1.27	0.55 - 0.61	0.895 - 0.910	0.55 - 0.60	1.00 - 1.20	1.24	1.08	0.90 - 1.29
Tensile Strength, psi	D-638	1500 - 4400	3900	1500 - 2150	540	2800 - 4400	250	>4800	6000	6000	1250 - 2200
Elongation %	D-412	38 - 395	240	175 - 590	165	650	100	530 - 750	490	500	490 - 730
Volume Resistivity, Ohm-cm	D-257	10 ¹³ - 10 ¹⁶	10 ¹⁴	>10 ¹⁴	10 ¹⁵	1.5 x 10 ¹⁴ 2.8 x 10 ¹⁴	10 ¹⁴	2 x 10 ¹² 11 x 10 ¹²	10 ¹⁰	10 ¹²	2 x 10 ¹⁶
Dielectric Strength, Volts/mil	D-149	240 - 490	390	220 - 1400	290	440 - 830	290	320 - 620	450	460	700
Dielectric Constant @ 1 kHz	D-150	3.7 - 8.1	2.9	2.28 - 2.55	1.7	2.2	1.7	5.7 - 7.7	3.8	4.6	2.8
Power Factor (Dissipation) @ 1 kHz	D-150	0.008 - 0.17	0.0038	0.00049	0.00035	0.0043	0.0034	0.043 - 0.060	0.018	0.045	0.0018
Abrasion Resistance		Good	Excellent	Good	Poor	Poor	Poor	Excellent	Excellent	Excellent	Good
Heat Resistance		Good	Good	Good	Poor	Good	Poor	Good	Good	Good	Good
Weatherability		Good	Good	Excellent	Poor	Excellent	Poor	Good	Excellent	Good	Good
Flame Retardancy		Excellent	Good	Poor	Poor	Poor	Poor	Fair	Poor	Poor	Good
Water Resistance		Good	Good	Excellent	Poor	Excellent	Poor	Good	Good	Fair	Good
Acid Resistance		Good	Good	Good	Fair	Excellent	Fair	Fair	Good	Good	Good
Alkali Resistance		Excellent	Excellent	Good	Fair	Excellent	Fair	Fair	Good	Good	Good
Aliphatic Hydrocarbon Resistance		Good	Good	Poor	Fair	Fair	Poor	Fair	Good	Good	Good
Aromatic Hydrocarbon Resistance		Poor	Poor	Poor	Fair	Fair	Poor	Poor	Good	Good	Good

Properties of Insulation Materials

Properties	Thermoset Neoprene	SBR	KYNAR®	PFA	TEFLON® FEP	TFE
Specific Gravity	1.21 - 1.60	0.92	1.74 - 1.77	2.13 - 2.16	2.13 - 2.16	2.13 - 2.20
Tensile Strength, psi	1175 - 2600	>2800	5000 - 7400	4000 - 4200	2600 - 3000	1100 - 3300
Elongation %	290 - 680	>430	500	300	260 - 320	265
Volume Resistivity, Ohm-cm	10 ¹⁰ - 10 ¹²	3 x 10 ¹⁵	2 x 10 ¹²	>10 ¹⁴	2 x 10 ¹⁶	>10 ¹⁶
Dielectric Strength, Volts/mil	590	400 - 500	250	480	480 - 550	500
Dielectric Constant @ 1 kHz	4.9 - 7.1	3	7.6	2.2	2.2	2.2
Power Factor (Dissipation) @ 1 kHz	3.6	0.0035	0.019	0.00003	0.0006	0.0002
Abrasion Resistance	Excellent	Good	Good	Fair	Good	Fair
Heat Resistance	Good	Fair	Excellent	Excellent	Excellent	Excellent
Weatherability	Good	Fair	Good	Good	Good	Excellent
Flame Retardancy	Good	Poor	Excellent	Excellent	Excellent	Excellent
Water Resistance	Excellent	Good	Good	Excellent	Good	Excellent
Acid Resistance	Good	Fair	Excellent	Excellent	Excellent	Excellent
Alkali Resistance	Good	Fair	Excellent	Excellent	Excellent	Excellent
Aliphatic Hydrocarbon Resistance	Good	Poor	Excellent	Excellent	Excellent	Excellent
Aromatic Hydrocarbon Resistance	Fair	Poor	Excellent	Excellent	Excellent	Excellent

Teflon® is a registered trademark of DuPont.